

Ventos SD Variable Membrane




The Innovative Moisture-Variable Vapour Barrier!

Properties:



Classification:



Product Data Sheet		
Material		PP.PP
Film		PP
Colour		White
Resistance under PTV		-
Mass per unit area	EN 1849-2	100 g/m ²
Thickness		0,30 mm
Sd value	EN ISO 12572	0,2 - 20 m
Water vapour permeability	EN ISO 12572	ca. 100 - 1 g/m ² /24 h
Water tightness	EN 13984	passed
Maximum tensile force MD/CD*	EN 12311-1	290 / 270 N/50 mm
Elongation MD/CD*	EN 12311-1	40 / 40 %
Tear resistance MD/CD*	EN 12310-1	55 / 60 N
Fire behaviour	EN 13501-1	E
Outdoor weathering		3 months
Temperature		-40°+100°C

*MD = longitudinal CD = transverse

** Also available in width 3m on request

Articles & Units				
Article	Article TOP SK	Width (m) **	Length (m)	Pallet (m ²)
1223.10065	-	1,5	50	2250



Edition: 2020: We reserve the right to review or change these technical values.

Disclaimer: no liability will be assumed if the product is not used as prescribed.